



**BUREAU
VERITAS**

TEST REPORT

TO: PROTEX CHEM
PLOT 40-SINDHI MUSLIM COOPERATIVE
HOUSING SOCIETY BLOCK B SINDHI
MUSLIM CHS (SMCHS), KARACHI

LAB NO.: (7326) 103-0241
FORM NO.: /
DATE IN: April 13, 2026
TESTING DATE: April 14, 2026
REVISED DATE: /
DATE OUT: April 28, 2026
BUYER: SELF REFERENCE
NO. OF WORKING DAYS: 04(SEE NOTE)
PAGE 1 OF 4

ATTN: MR. ALTAF PAREKH

OVERALL RATING

PASS _____
FAIL _____
DATA _____ **X**

Vendor:	PROTEX CHEM	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	PROTEX CHEM
P.O. No.:	/	Style No.:	/
Sample Description:	MARK G/NZC SK (GOAT WATERPROOF)	Style Description:	/
Color:	YELLOW	Country of Origin:	PAKISTAN
Fabric Weight:	/	Claimed Fabric Count:	/
Buyer's Name	/	Submitted Size:	A4 SIZE
Size Range:	/	Finishing:	/
GPU No.:	/	End Use:	/

Product Category:	LEATHER SWATCH
Test Requested:	SPECIFIC TEST SEE PROPERTY LIST
Previous Report No.:	/

Submitted Fiber Content:	/
Actual Fiber Content:	/
Suggested Fiber Content:	/
Submitted Care Instruction(s):	/
Client Expected Care Instruction:	/
Suggested Care Instruction(s):	/

BV Consumer Products Services Pakistan Pvt. Ltd.
191-S, Quaid-i-Azam Industrial Estate Area,
Kot Lakpath, Township, Pakistan.
Tel: +92-42-35215779-83 Fax: +92-42-35215787
EXT-195

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
RESISTANCE OF GLOVE MATERIALS TO WATER ABSORPTION	X			

NOTE: THE SAMPLE WAS SUB-CONTRACTED TO BV CHINA ON "RESISTANCE OF GLOVE MATERIALS TO WATER ABSORPTION" AND AFTER RECEIVING RESULTS ON APRIL 27, 2026. THE REPORT IS BEING RELEASED.

**TECHNICAL
QUESTIONS:**

Ejaz.Ahmed
Dir.: (+92-42) 35215786 | Fax: (+92-42) 35215787|
Cell: +92300-0540972
ejaz.ahmed@bureauveritas.com

Abid Ali
Ph#: (+92-42) 35215779 (Ext: 143) |
Cell: +92324-9444001
Abid.ali@bureauveritas.com

**GENERAL
INFORMATION:**

Salman Yousaf (CS)
Ph#: (+92-42) 35215779 | Fax: (+92-42) 35215787|
Cell: +92324-9444002
Salman.yousaf@bureauveritas.com

Signatures: BV Consumer Product Services Pakistan Pvt. Ltd.



Ejaz Ahmed Dept. Program Manager (US-2)

TEST RESULTS		
TEST PROPERTY		REQUIREMENTS

TEST ITEM/METHOD	Water penetration and water absorption (Upper) (ISO 5403-1)
-------------------------	---


Condition: <u>50 %RH</u> , From <u>4.23</u> to <u>4.24</u> , Total <u>24</u> Hours(min.24h)

AFTER 180 MINUTES:

Sample	Size/Sample	Water absorption			Water penetration		
		M ₂ (g)	M ₁ (g)	WA	P ₂ (g)	P ₁ (g)	WP
	Sample 1(#)	2.6812	2.2828	17.5%	1.4814	1.3952	0.19g
	Sample 2(#)	2.6533	2.2764	16.6%	1.4725	1.4012	0.07g
	AVG			17.0%			0.08g

#: NO OBVIOUS WATER PENETRATION

DIGITAL PICTURE



*****END OF TEST REPORT*****